

What is claimed is:

1. A fiber reinforced plastic pipe reduced in
thickness and increased in diameter by pultrusion process,
5 comprising

a fiber bundle spun and aligned in a longitudinal
direction, and

circumferential reinforced fiber sheet provided at
least either on an outer surface layer or on an inner
10 surface layer thereof.

2. A fiber reinforced plastic pipe reduced in
thickness and increased in diameter by pultrusion process,
comprising

15 a fiber bundle spun and aligned in a longitudinal
direction, and

circumferential reinforced fiber sheet provided at
least either on an outer surface layer or on an inner
surface layer thereof, wherein

20 the pipe has a slit, capable of being reduced in
diameter along the circumference, provided in the
longitudinal direction, such that said fiber reinforced
plastic pipe can be inserted into a metal pipe.

25 3. The fiber reinforced plastic pipe according to

claim 1 or 2, wherein

a tensile elasticity of fibers forming said fiber bundle is 196GPa or more.

5 4. The fiber reinforced plastic pipe according to claim 1 or 2, wherein

a tensile elasticity of fibers forming said circumferential reinforced fiber sheet is 58.8GPa or more.

10 5. The fiber reinforced plastic pipe according to claim 1 or 2, wherein

a basis weight (FAW) of said circumferential reinforced fiber sheet is in the range of 100g/m² to 600g/m².

15 6. The fiber reinforced plastic pipe according to claim 1 or 2, wherein

a thickness of said circumferential reinforced fiber sheet is in the range of 0.05mm to 1.0mm.

20 7. A power transmission shaft comprising a metal joint element and a metal pipe jointed to each other, wherein

the shaft further comprises a fiber reinforced
25 plastic pipe inserted into said metal pipe, said fiber

reinforced plastic pipe being reduced in thickness and increased in diameter by pultrusion process, comprising a fiber bundle spun and aligned in a longitudinal direction, and circumferential reinforced fiber sheet provided at least either on an outer surface layer or on an inner surface layer thereof.

8. A power transmission shaft comprising a metal joint element and a metal pipe jointed to each other, wherein

the shaft further comprises a fiber reinforced plastic pipe inserted into said metal pipe, said fiber reinforced plastic pipe being reduced in thickness and increased in diameter by pultrusion process, comprising a fiber bundle spun and aligned in a longitudinal direction, and circumferential reinforced fiber sheet provided at least either on an outer surface layer or on an inner surface layer, the pipe having a slit, capable of being reduced in diameter along the circumference, provided in the longitudinal direction.

9. The power transmission shaft according to claim 8, wherein the slit has a width of 0.01% or more and 40% or less of the outer circumference thereof in a natural state.

10. The power transmission shaft according to claim 8 or 9, wherein said slit has a bias angle within ± 30 degrees with respect to an axial direction of said fiber reinforced plastic pipe.

5

11. The power transmission shaft according to claim 8, wherein a value of D_1/D_2 is greater than 1 and equal to 1.3 or less, where D_1 is an outer diameter of said fiber reinforced plastic pipe and D_2 is an inner diameter of said metal pipe.

10

12. The power transmission shaft according to claim 7 or 8, wherein

a tensile elasticity of fibers forming said fiber bundle is 196GPa or more.

15

13. The power transmission shaft according to claim 7 or 8, wherein

a tensile elasticity of fibers forming said circumferential reinforced fiber sheet is 58.8GPa or more.

20

14. The power transmission shaft according to claim 7 or 8, wherein

a basis weight (FAW) of said circumferential reinforced fiber sheet is in the range of 100g/m² to

25

600g/m².

15. The power transmission shaft according to claim 7
or 8, wherein

5 a thickness of said circumferential reinforced fiber
sheet is in the range of 0.05mm to 1.0mm.

16. The power transmission shaft according to claim 7
or 8, wherein

10 said fiber reinforced plastic pipe has a layered
structure of 20 layers or less.

17. The power transmission shaft according to claim 7
or 8, wherein

15 a value of FL/PL is 0.1 or more and 1.0 or less,
where PL is a length of said metal pipe and FL is a length
of said fiber reinforced plastic pipe.

18. The power transmission shaft according to claim 7
20 or 8, wherein

 a value of t_2/t_1 is 0.01 or more and 10 or less,
where t_1 is a thickness of said metal pipe and t_2 is a
thickness of said fiber reinforced plastic pipe.

25 19. The power transmission shaft according to claim 7

or 8, wherein

said fiber reinforced plastic pipe is fixed to said metal pipe by reducing said metal pipe in diameter along the outer circumference by plastic-working, with said fiber reinforced plastic pipe being inserted in said metal pipe.

20. The power transmission shaft according to claim 7 or 8, wherein

said fiber reinforced plastic pipe is fixed to said metal pipe with an adhesive.

21. The power transmission shaft according to claim 20, wherein

a recessed portion for accommodating adhesive is provided at least on any one of an outer circumference of said fiber reinforced plastic pipe or an inner circumference of said metal pipe.